

Product name	Chemical composition, %		Sieve Analysis, %		Density, g/cm <sup>3</sup>	Humidity (H <sub>2</sub> O), %
<b>Iron powder AIP 3.200A</b>	C	≤0,08	+400 μm	0,0	3,49-3,86	≤0,5
	Si	≤0,1	+355 μm	≤2,0		
	Mn	≤0,4	+160 μm	20-30		
	S	≤0,020	+63 μm	40-50		
	P	≤0,035	-63 μm	≤30,0		
<b>Iron powder AIP 3.315A</b>	C	≤0,08	+400 μm	0,0	3,74-4,26	
	Si	≤0,1	+355 μm	≤2,0		
	Mn	≤0,4	+160 μm	30-45		
	S	≤0,020	+63 μm	35-50		
	P	≤0,035	-63 μm	≤20,0		
<b>Feromangane se Powder FeMn80</b>	Mn	79-83	+400 μm	0,0	3,15-3,56	
	C	≤1,5	+355 μm	≤2,0		
	Si	≤2,0	+200 μm	15-35		
	S	≤0,015	+63 μm	45-65		
	P	≤0,035	-63 μm	≤25,0		